

SUGGESTED APPLICATIONS TEMPERATURES

The following values are based on what we feel provides optimal results for spray applications.

Degrees in Fahrenheit

<u>Emulsions</u>	<u>Minimum</u>	<u>Maximum</u>
CHFRS-2P	130	180
CNTT	150	180
CPEM-1	120	175
CRS-2	125	180
CRS-2P	130	180
CSS-1H	120	160
CSS-1HP	120	160
EA-90	125	180
EA-90P	130	180
EA-150/EA-300	130	180
HFE-90	125	180
HFE-150/EA-300	130	180
HFRS-2	130	180
HFRS-2P	150	180
NTEA	150	180
PEP	70	180
RSP	120	175
SS-1H	120	160
SS-1HP	120	175
SS-1VH	150	180